

Taino International Inc.

ATLANTIC TALC 50

Product Data Sheet

Typical Properties

Brightness (ISO)/ Whiteness	79-83 %
Bulk Density (LOOSE) (DIN 468)	300-380 gm/liter
Oil Absorption (ISO 787/5)	45-51 gm/100gm
pH (10% aq. Slurry) (ISO 787-9)	8.5-9.5
PSD-D (50)-50% particles below	2.0-4.0 μ
PSD-D (97)-97% particles below	9.0-15.0 μ
Moisture (ISO 787-2)	0.0-0.2 %
Residue on 500 mesh	0.0-0.2 %
Specific gravity (ISO 787/10)	2.6-2.8
L* (CIE)	95.19
a* (CIE)	-0.27
b* (CIE)	2.02